

# SIGMACOVER™ 246

## DESCRIPTION

Two-component, polyamide high-build epoxy primer/buildcoat, containing zinc phosphate

## PRINCIPAL CHARACTERISTICS

- General-purpose epoxy coating in protective coating systems for the protection of steel structures in atmospheric exposure
- Good adhesion to steel
- Good flow and wetting properties
- Easy application by airless spray
- Cures at temperatures down to 5°C (41°F)
- Good performance on top of zinc silicate primers

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.7 lb/US gal)
Volume solids	64 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 241.0 g/kg UK PG 6/23(92) Appendix 3: max. 337.0 g/l (approx. 2.8 lb/US gal) China GB 30981-2020 (tested) 247.0 g/l (approx. 2.1 lb/gal)
Recommended dry film thickness	75 - 150 µm (3.0 - 6.0 mils)
Theoretical spreading rate	8.5 m <sup>2</sup> /l for 75 µm (342 ft <sup>2</sup> /US gal for 3.0 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 10 hours Maximum: 6 months
Full cure after	7 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Steel; blast cleaned to ISO-Sa2½ or power tool cleaned to min. ISO-St3
- Zinc silicate primer; (SIGMAZINC 158, SIGMAWELD 165 or SIGMAWELD 199) a mist coat is required

# SIGMACOVER™ 246

## **Substrate temperature**

- Substrate temperature during application and curing should be above 5°C (41°F)
  - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- 

## **INSTRUCTIONS FOR USE**

### **Mixing ratio by volume: base to hardener 4:1**

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
  - Adding too much thinner results in reduced sag resistance and slower cure
  - Thinner should be added after mixing the components
  - On top of zinc silicates (SIGMAZINC 158) a special spray technique is needed: application of two coats wet on wet with a flash off time of approx. 2 minutes in between
- 

### **Pot life**

8 hours at 20°C (68°F)

Note:

- See additional data
- 

### **Airless spray**

#### **Recommended thinner**

THINNER 91-92

#### **Volume of thinner**

0 - 10%, depending on required thickness and application conditions

#### **Nozzle orifice**

Approx. 0.46 – 0.53 mm (0.018 – 0.021 in)

#### **Nozzle pressure**

14.0 - 25.0 MPa (approx. 140 - 250 bar; 2031 - 3626 p.s.i.)

---

# SIGMACOVER™ 246

## Brush/roller

- Application by brush may show brush marking, due to the thixotropic nature of the paint and is most suitable to small areas, tight angle areas or for stripe coating or touch-up
- Application by roller will leave roller marking and is suitable for minimum DFT requirements only
- A roller suitable for epoxy application must be used

## Recommended thinner

THINNER 91-92

## Volume of thinner

0 – 5%

## ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
75 µm (3.0 mils)	8.5 m <sup>2</sup> /l (342 ft <sup>2</sup> /US gal)
100 µm (4.0 mils)	6.4 m <sup>2</sup> /l (257 ft <sup>2</sup> /US gal)
150 µm (6.0 mils)	4.3 m <sup>2</sup> /l (171 ft <sup>2</sup> /US gal)

Overcoating interval for DFT up to 150 µm (6.0 mils)					
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	24 hours	10 hours	8 hours	6 hours
	Maximum	3 months	3 months	3 months	3 months
		None	None	None	None

### Notes:

- This product has an unlimited overcoating interval provided the surface is free from chalking and other contaminations
- In cases of exposure to direct sunlight or when the surface is contaminated it is recommended that the surface be cleaned and roughened to ensure good adhesion of the subsequent coating.
- The optimum intercoat adhesion is obtained when the subsequent coating is applied before the full cure time of the previous coating has elapsed

# SIGMACOVER™ 246

Curing time for DFT up to 100 µm (4.0 mils)			
Substrate temperature	Full cure	Dry to touch	Dry to handle
5°C (41°F)	20 days	12 hours	24 hours
10°C (50°F)	14 days	7 hours	18 hours
15°C (59°F)	10 days	5 hours	12 hours
20°C (68°F)	7 days	3 hours	6 hours
30°C (86°F)	3 days	2 hours	4 hours
40°C (104°F)	48 days	1 hour	3 hours

Note:

- Adequate ventilation must be maintained during application and curing

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	16 hours
15°C (59°F)	12 hours
20°C (68°F)	8 hours
25°C (77°F)	6 hours
30°C (86°F)	4 hours
40°C (104°F)	2 hours

## SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

- Information sheet | Explanation of product data sheets



# SIGMACOVER™ 246

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

---

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

---

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

