

PPG SIGMASHIELD® 680

DESCRIPTION

Two-component, epoxy anticorrosive primer, based upon pure epoxy technology

PRINCIPAL CHARACTERISTICS

- Specialized for use under SIGMAGLIDE fouling release system
- Excellent anticorrosive properties and water resistance
- Good abrasion resistance
- Suitable for application and curing in a wide range of climatic conditions
- Excellent adhesion to steel and non-ferrous metals

COLOR AND GLOSS LEVEL

- Gray, yellow/green and redbrown
- Low sheen

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.7 lb/US gal)
Volume solids	60 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 287.0 g/kg max. 392.0 g/l (approx. 3.3 lb/US gal)
Recommended dry film thickness	150 µm (6.0 mils)
Theoretical spreading rate	6.0 m ² /l for 100 µm (241 ft ² /US gal for 4.0 mils)
Dry to touch	2 hours
Full cure after	7 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

PPG SIGMASHIELD® 680

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Previous coat must be sound, dry and free from any contamination
- Surface must be free from grease, salts and any contamination
- Steel; blast cleaned to ISO Sa2½, blasting profile 30 – 75 µm (1.2 – 3.0 mils) or according to ISO St3
- Shop primed steel; pretreated to SPSS Pt3
- Coated steel; hydrojetted to VIS WJ2L (blasting profile 30 – 75 µm (1.2 – 3.0 mils))
- Aluminium substrate; - Dry & free from contamination. Pretreated by eccentric sanding or sweep-blasting with non-metallic / inert blasting material to a min. surface roughness of (Rz) 30-75 microns. To be coated within 6-8 hours

Substrate temperature and application conditions

- Substrate temperature during application and curing should be between 5°C (41°F) and 40°C (104°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- Relative humidity during application and curing should not exceed 85%

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 4:1

- The temperature of the mixed base and hardener should preferably be above 5°C (41°F), otherwise extra thinner may be required to obtain application viscosity
- Thinner should be added after mixing the components
- Adding too much thinner results in reduced sag resistance

Application

Pot life

4 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life

PPG SIGMASHIELD® 680

Air spray**Recommended thinner**

THINNER 91-92

Volume of thinner

0 - 15%, depending on required thickness and application conditions

Nozzle orifice

1.5 - 2.0 mm (approx. 0.060 - 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray**Recommended thinner**

THINNER 91-92

Volume of thinner

0 - 15%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.53 - 0.74 mm (0.021 - 0.029 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller**Recommended thinner**

No extra thinner is necessary

Volume of thinner

Up to 5% THINNER 91-92 can be added if desired

PPG SIGMASHIELD® 680

ADDITIONAL DATA

Overcoating interval for DFT up to 150 µm (6.0 mils)							
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
SIGMAGLIDE 790	Minimum	28 hours	24 hours	20 hours	12 hours	10 hours	8 hours
	Maximum	7 days	7 days	6 days	5 days	4 days	2 days
itself	Minimum	13 hours	6 hours	4 hours	3 hours	2 hours	1 hour
	Maximum	1 months	1 months	1 months	14 days	14 days	14 days

Note:

- Surface should be dry and free from any contamination

Curing time for DFT up to 150 µm (6.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	4 hours	8 hours	9 days
10°C (50°F)	3 hours	6 hours	7 days
15°C (59°F)	2 hours	4 hours	5 days
20°C (68°F)	2 hours	3 hours	4 days
30°C (86°F)	1 hour	2 hours	3 days
40°C (104°F)	1 hour	2 hours	2 days

Note:

- Adequate ventilation must be maintained during application and curing

Pot life (at application viscosity)	
Mixed product temperature	Pot life
5°C (41°F)	10 hours
10°C (50°F)	7 hours
15°C (59°F)	6 hours
20°C (68°F)	4 hours
30°C (86°F)	2 hours
40°C (104°F)	1 hour

PPG SIGMASHIELD® 680

SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.