

SIGMASHIELD™ 880 ALU

DESCRIPTION

Two-component, surface tolerant high solid MIO / Aluminium epoxy primer

PRINCIPAL CHARACTERISTICS

- Primarily designed as primer for use in harsh conditions like offshore splash zone and subsea
- Outstanding sea water resistance
- Excellent corrosion resistance
- Excellent abrasion and impact resistance
- Continues to cure when immersed in water
- Resistant to well designed cathodic protection
- Perfect for buried pipes and structural steel in heavy industrial areas
- Meets the requirements of Norsok M-501 Rev. 6, System 7A, 7B and 7C
- Meets the requirements of ISO 12944-9, splash and tidal zones (CX and Im4) and immersion (Im4)

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.5 kg/l (12.1 lb/US gal)
Volume solids	85 ± 2%
VOC (Supplied)	max. 220.0 g/l (approx. 1.8 lb/US gal)
Recommended dry film thickness	150 - 1000 µm (6.0 - 40.0 mils) depending on system
Theoretical spreading rate	4.3 m ² /l for 200 µm (170 ft ² /US gal for 8.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 3.5 hours Maximum: 14 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

SIGMASHIELD™ 880 ALU

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Coating performance will depend upon the surface preparation degree
- Steel; blast cleaned to ISO-Sa2 or ISO-Sa2½
- Blasting profile of 40 – 80 µm (1.6 – 3.1 mils) is recommended
- Steel; hand/power tool clean in accordance with St3 or SSPC-SP3 for new building and St2 or SSPC-SP2 for maintenance, UHPWH in accordance with WJ-2L/3L (SSPC-VIS-4)
- Compatible previous coat must be dry and free from any contamination

Note:

- For subsea service at high operating temperatures (up to 90°C / 194°F), abrasive blast cleaned to minimum ISO-Sa2½ (SSPC SP-10), blasting profile 40 – 80 µm (1.6 – 3.1 mils)
-

Substrate temperature

- Substrate temperature during application should be at least 3°C (5°F) above dew point
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 3:1

- Thinner should be added after mixing the components
 - Do not thin more than is required by appropriate application property
 - Adding too much thinner results in reduced sag resistance and slower cure
-

Pot life

2 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life
-

SIGMASHIELD™ 880 ALU

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

4 - 8%, depending on required thickness and application conditions

Nozzle orifice

1.5 - 3.0 mm (approx. 0.060 - 0.110 in)

Nozzle pressure

0.2 - 0.4 MPa (approx. 2 - 4 bar; 29 - 58 p.s.i.)

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 8%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.53 - 0.69 mm (0.021 - 0.027 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 5%

SIGMASHIELD™ 880 ALU

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
175 µm (7.0 mils)	4.9 m ² /l (195 ft ² /US gal)
300 µm (12.0 mils)	2.8 m ² /l (114 ft ² /US gal)
500 µm (20.0 mils)	1.7 m ² /l (68 ft ² /US gal)

Overcoating interval for DFT up to 500 µm (20.0 mils)						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself and SIGMASHIELD 880	Minimum	14 hours	7 hours	3.5 hours	2 hours	1.5 hours
	Maximum	1.5 month	1 month	28 days	21 days	14 days

Note:

- Surface should be dry and free from any contamination

Curing time for DFT up to 500 µm (20.0 mils)			
Substrate temperature	Full cure	Dry to touch	Dry to handle
-5°C (23°F)	30 days	24 hours	48 hours
5°C (41°F)	18 days	10 hours	24 hours
10°C (50°F)	14 days	5 hours	16 hours
20°C (68°F)	7 days	3 hours	8 hours
30°C (86°F)	5 days	2 hours	5 hours
40°C (104°F)	3 days	1 hour	3 hours

Notes:

- For repair of jetties, piling etc. between tides, SIGMASHIELD 880 ALU can be immersed within 30 minutes. Whitening can be happened, but will not affect anti-corrosive performances.
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- The curing time is related to the DFT of the paint and ventilation of the drying condition. High DFT and poor ventilation will slow curing
- At DFT ranging from 500 – 1000 µm (20.0 – 40.0 mils) applied in a one coat application, curing times have to be 2 - 2.5 times in order to obtain sufficient mechanical strength

SIGMASHIELD™ 880 ALU

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	3 hours
20°C (68°F)	2 hours
30°C (86°F)	1 hour

Product Qualifications

- Qualified for NORSOK M501 Rev.6 System 7A with 2 coating system
- Qualified for NORSOK M501 Rev.6 System 7C up to 90°C(194°F) with 2 coating system, which can be used as NORSOK M501 System 7B as well

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

