

PPG STEELGUARD® 652 G

DESCRIPTION

One-component, thin-film, waterborne intumescent coating for fire protection of structural steelwork

PRINCIPAL CHARACTERISTICS

- Provides up to 180 minutes protection from cellulosic fires
- On-site application
- Up to 700 µm (28.0 mils) DFT in a single coat
- Independently tested and approved in accordance to China national standard GB14907

COLOR AND GLOSS LEVEL

- White
- Matt

BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Mass density	1.41 kg/l (11.77 lb/US gal)
Volume solids	70 ± 3%
VOC (Supplied)	EPA Method 24: 0.0 lb/US gal (3.1 g/l)
Recommended dry film thickness	150 - 700 µm (6.0 - 28.0 mils) per coat
Theoretical spreading rate	1.00 m ² /l for 700 µm (40 ft ² /US gal for 28.0 mils)
Dry to touch	1 hour
Overcoating Interval	Minimum: 3 hours Maximum: Unlimited
Shelf life	At least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time
- The required dry film thickness must be in accordance with the approval certification
- Materials should be stored in dry conditions, out of direct sunlight and at temperature between 10°C (50°F) and 30°C (86°F). Shelf life may be reduced by storage at low temperatures, material must not be allowed to freeze.

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Approved primer must be sound, dry, free from any contamination and the surface prepared in accordance with PPG STEELGUARD 652 G APPLICATION GUIDELINES



PPG STEELGUARD® 652 G

Substrate temperature and application conditions

- Substrate temperature during application and curing should be between 10°C (50°F) and 40°C (104°F)
- Substrate temperature during application and curing should be at least 3°C (37°F) above dew point
- Ambient temperature during application and curing should be between 10°C (50°F) and 40°C (104°F)
- Relative humidity during application and curing should not exceed 80%

Note:

- Over application will extend drying/curing times. Care should be taken in areas such as flange/web interfaces as excessive film build can result in small hairline cracks. This cracking will not affect the fire performance of the material.

INSTRUCTIONS FOR USE

- Application should be in accordance with PPG STEELGUARD 652 G APPLICATION GUIDELINES
- Stir thoroughly until homogeneous and free of lumps
- Adding too much water results in reduced sag resistance and slower cure
- Must be protected from freezing at all times during storage and/or transport

Airless spray

Recommended thinner

Tap water (normally no thinner required)

Volume of thinner

0 – 5%

Nozzle angle

20° – 50°, depending on shape of steel parts

Nozzle orifice

Approx. 0.43 – 0.53 mm (0.017 – 0.021 in)

Nozzle pressure

20.0 MPa (approx. 200 bar; 2901 p.s.i.)

Notes:

- See PPG STEELGUARD 652 G APPLICATION GUIDELINES for full details
- All filters, including surge bottle and gun filters to be removed
- External fluid uptake pipe filter is recommended

PPG STEELGUARD® 652 G

Brush/roller

- For small areas only (touch up and repair)

Recommended thinner

No thinner should be added

Cleaning solvent

- Tap water

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
200 µm (8.0 mils)	3.50 m ² /l (140 ft ² /US gal)
400 µm (16.0 mils)	1.75 m ² /l (70 ft ² /US gal)
500 µm (20.0 mils)	1.40 m ² /l (56 ft ² /US gal)
700 µm (28.0 mils)	1.00 m ² /l (40 ft ² /US gal)

Note:

- Maximum DFT when brushing: 400 µm (16.0 mils)

Overcoating interval for DFT up to 700 µm (28.0 mils)					
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	4 hours	3 hours	2 hours	1.5 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited
approved topcoats	Minimum	24 hours	20 hours	18 hours	14 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited

Notes:

- Prior to application of a topcoat, the applicator must ensure that the specified dry film thickness has been achieved
- The system should be dry to handle and coating thickness gauge should not to leave an indentation on the surface prior to applying subsequent coats. Curing time(s)/overcoating interval(s) may be extended at higher applied DFT's and/or there is a change in environmental conditions.
- All overcoating times have been measured at an intumescent WFT of 1000 µm (approx. 700 µm DFT) under controlled temperature and relative humidity below 80%. Higher thicknesses will take longer to cure.

PPG STEELGUARD® 652 G

Curing time for DFT up to 700 µm (28.0 mils)	
Substrate temperature	Dry to touch
10°C (50°F)	1.5 hours
20°C (68°F)	1 hours
30°C (86°F)	30 minutes
40°C (104°F)	10 minutes

Note:

- All curing times have been measured at an intumescent WFT of 1000 µm (approx. 700 µm DFT) under controlled temperature and relative humidity below 80%. Higher thicknesses will take longer to cure.

SAFETY PRECAUTIONS

- Although this is a waterborne paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- Read all label and Safety Data Sheet (SDS) information prior to use

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets
- System sheet | PPG STEELGUARD | Approved topcoats
- System sheet | PPG STEELGUARD | Approved primers
- System sheet | PPG STEELGUARD | Systems and environments

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

